

... ( ) = ( ) - 2015. - 1 (84). - .186-192

« . »  
 1  
 2  
 3

( )  $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_{(n-1)}\text{Cu}_n\text{O}_y$  (n=3-9) ,

(Al<sub>2</sub>Ti<sub>5</sub>)

$\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$


= 1, 2)  $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_{(n-1)}\text{Cu}_n\text{O}_y$  (n  
 120-140 - ,

( )


( )

[1-4].

$1 \cdot 10^4$   
/ 2



[5-7].



[8].

« »


$10^4-10^5$  /

[9, 10].

- 1

C

2



(2223)

120 - 180 ( )


1,5

, 60

850-852° -




ASTM [The American Mineralogist Crystal Database]



$a = 5,3990$  ,  $b = 5,413$   
 $c = 37,130$  , 2223 -

(1- ).



1-  $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$  - , 60  
(2223) 850-852° -

60 5 5 ,


$\text{Al}_2\text{O}_3$

(56,08 %) -TiO<sub>2</sub> (43,92 %) -  
 MgO (5 %) - SiO<sub>2</sub> (5%)

1350 - 1375° - 2

, - Al<sub>2</sub> TiO<sub>5</sub>

(2 - ).



2-

Al<sub>2</sub>TiO<sub>5</sub>, 1350 - 1375° -

(Al<sub>2</sub>TiO<sub>5</sub>)

Bi<sub>1,7</sub>Pb<sub>0,3</sub>Sr<sub>2</sub>Ca<sub>2</sub>Cu<sub>3</sub>O<sub>y</sub>,

, [120] [202]

( 2 )

Bi<sub>1,7</sub>Pb<sub>0,3</sub>Sr<sub>2</sub>Ca<sub>2</sub>Cu<sub>3</sub>O<sub>y</sub> (2223),

~150-170

100

, 5-10



850° - , 48

Bi<sub>1,7</sub>Pb<sub>0,3</sub>Sr<sub>2</sub>Ca<sub>(n-1)</sub>Cu<sub>n</sub>O<sub>y</sub> (n = 1, 2, 4)

105-110



(3 - ).

(3- ).




3-  $Al_2Ti_5$




48, 850°



4-



4- 850°, 48




150-160



, 850°

48

(5- ).



5- .  $\text{Al}_2\text{Ti}_5$   
 $\text{Bi}_{1.7}\text{Pb}_{0.3}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$  ,  $850^\circ$  , 48



6-  $\text{Al}_2\text{Ti}_5$   
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_5\text{Cu}_6\text{O}_y$  ( )  
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_8\text{Cu}_9\text{O}_y$  ( ) ,  
 $850^\circ$  , 48

$\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_{(n-1)}\text{Cu}_n\text{O}_y$  (n=6-9)  
 Ca Cu  
 , ASTM [11,12]  
 , 2212 2223

( $\text{Al}_2\text{Ti}_5$ )  
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_{(n-1)}\text{Cu}_n\text{O}_y$   
 (n=3-9)  
 3-6 - (1)

$\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$   
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{CaCu}_2\text{O}_y$   
 ( )  
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{CaCu}_2\text{O}_y$   
 (2212) -  $\text{Al}_2\text{TiO}_5$   
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$  (2223)  
 -  $\text{Al}_2\text{TiO}_5$

$\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$  (2223)  
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{CaCu}_2\text{O}_y$   
 (2212)  
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$  (2223)  
 -  $\text{Al}_2\text{TiO}_5$


$\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{CaCu}_2\text{O}_y$  (2212)  
 $\text{Al}_2\text{TiO}_5$   
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_{(n-1)}\text{Cu}_n\text{O}_y$  (n=3-9)

$\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_{(n-1)}\text{Cu}_n\text{O}_y$  (n=3-9)  
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{CaCu}_2\text{O}_y$  (2212)  
 $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$  (2223)


$\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_3\text{Cu}_4\text{O}_y$  (2234)

1. . . . .  
 $\text{Bi}_{2-x}\text{Pb}_x\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$  ( $0,2 < x < 0,4$ ) //  
: , , . 1990, .3, 2, . 298-307.
2. . . . .  
-  $\text{Bi-Sr-Ca-Cu-O}$ ,  
2-2-1-2 // . 1993, .29, 12,  
. 1683-1985.
3. . . . .  
//  
. 1993, .29, 12, .1571-1581.
4. . . . .  
 $(\text{Bi,Pb})\text{-Sr-Ca-Cu-O}$  (2223) // : , , .  
1992, T.5, 11, C.2072-2077.
5. . . . .  
- //  
. 2000, 1-3 - .
6. . . . .  
// : . 2001,  
T. 71, 4, C. 303-319.
7. . . . .  
// : , , . 1992, T. 5, 8,  
C.1351-1367.
8. . . . . // . « . » .  
1991, C. 126-137.
9. . . . .  
// . “ ” . 1989, C. 12-27.
10. Sastri P., Yakhsmi J., Iyer R. //Bull. Mater. Sci. 1991, V.14.  
P.223-226.
11. Sequeira A., Rajagopal H., Sastry P., Yakhmi J., Iyer R. Physica C:  
Superconductivity. 1991, V.173, P. 267-269.
12. Jian C., Zuyao C., Yitai Q., Jiansheng X., Zhenghui H., Shifong S.,  
Minhu F., Qirui Z. Solid. Stat. Commun. 1988, V.68, P. 327-230.





( $\text{Al}_2\text{Ti}_5$ ).



120-140

### Resume

The article explores the possibility of obtaining a textured polycrystalline high-temperature superconducting ceramic coating on highly anisotropic structure. The synthesis of superconducting coating carried by the nominal compositions of amorphous precursor  $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_{(n-1)}\text{Cu}_n\text{O}_y$  ( $n=3-9$ ) which are obtained by quenching the melt under the influence of radiant heat and with a pre-synthesized using high-temperature superconducting phases of the ceramic substrate, aluminum titanate ( $\text{Al}_2\text{TiO}_5$ ). The study did not find that significant differences in the phase composition of the synthesized coatings. In all coatings the main phase is superconducting phase  $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$ , wherein the superconducting phase present  $\text{Bi}_{1,7}\text{Pb}_{0,3}\text{Sr}_2\text{Ca}_{(n-1)}\text{Cu}_n\text{O}_y$  ( $n = 1, 2$ ) having a low critical temperature. Texture of the particles of the superconducting coating was installed. Texturing of the coating is broken with increasing coating thickness of 120-140  $\mu\text{m}$  and above.